


BAU 08

High performance, water repellent tile grout with a smooth and uniform surface.



Description

High performance, water repellent cement based tile grout for smooth and uniform surface. Offers high mechanical strength, superb color stability and great water-repellency, with special components that prevent the development of bacteria. Ideal for all kind of ceramic tiles, granite, glass mosaic and natural stone, for indoors and outdoors use on walls and floors.

Suitable for joints 1-15 mm wide

Materials:

All types of ceramic tiles, Grès, Porcellanato, clinker, cotto, marble-style ceramic granite, ceramic mosaic, all sizes of tiles, natural stone, marble, etc.

Substrates:

- Walls and floors
- Indoor and outdoor areas
- Residential, commercial and industrial applications
- Bathrooms, balconies, tanks, swimming pools
- Underfloor heating

Surface preparation

Apply tile grout, ensuring that the recommended waiting period before grouting - as required by the bonding agent - is met. In case cladding is fixed with mortar, leave the surface for at least 14 days before tiling grouting. After thorough drying of the tile adhesive and provided that tiles are fixed in their final positions, clean joints well prior to application. Remove foreign particles such as tile spacers, adhesive residue, dirt, etc. Possible rising moisture may cause salt deposits on the surface and variation of colour.

Highly absorbent tiles

For surfaces exposed to extreme solar radiation and during extreme summer heat or in case substrate is excessively absorbent, to reduce water absorption, we recommend that clearances are lightly wetted with a sponge – without saturation - before caulking. On tiles whose surface is extremely absorbent or porous, cleaning can be difficult; in such cases, trial application is recommended.



Mixture preparation

The material must be prepared in a suitable container; first pouring approximately $\frac{3}{4}$ of the required quantity of water and then gradually adding the contents of the bag, whilst stirring with an electric mixer at low speed. Then add water until a uniform mixture with the required makeup is obtained. The quantity of mixing water written on the packaging is only indicative. You may add a commensurate quantity of water for more or less thixotropic composition, depending on the intended application. Prepare all the mixtures of the same project with equal quantities of water to prevent colour variation. **Caution:** Adding more water than the prescribed ratio may result in colour deterioration during curing, and a reduction in the strength of the mortar.

Instructions for use

Apply the mixture on the surface to be grouted. Spread the material in diagonal streaks, cross-wise to the joints using a rubber spatula; press into the joints to make sure that spaces are completely filled. Immediately remove rough residue with the spatula. Allow 1 to 1.5 hours to pass; the material will start drying (dulling on the tiles). Then clean tiles with a lightly damp sponge, thus finishing the surface. Then, after joints have completely cured, finish with a soft cloth to allow them to take their final form.


Storage

Preferably in shady and roofed locations, low in moisture, for at least 12 months

Product specifications


Classified according to European standard EN 13888. Heavy duty cement-based tile grout in accordance with group CG2WA

TDS_BAU 08_12.2022



BAU 08

High performance, water repellent tile
grout with a smooth and uniform surface.



Technical features

Form:
dry powder in 26 shades

Mortar density:
1.2 kg/L

Mixing water:
≈1.5 L / 1 5kg bag

Mix pot life:
approximately 1,5 hours

Application temperature:
+5°C to +35°C

Bonding strength per EN 12808 (N/mm²)
Flexural strength in 28 days:
≥ 8.0 N/mm²
Compression strength in 28 days:
≥30.0 N/mm²
Resistance to freezing / thawing cycles
Flexural strength : ≥ 7.0 N/mm²
Compression: ≥ 30.0 N/mm²
Water absorption after 30 minutes:
≤ 0.1 g
Water absorption after 240 minutes:
≤ 0.2 g

Temperature resistance:
-40° C to +90° C

Ready to use:
after 3 days

Consumption

Grans / m ² / joint width		Joint width				
		1mm	2mm	3mm	5mm	8mm
Tile Dimension in cm						
2 x 2 x 0,3		550	1100	1650	-	-
5 x 5 x 0,4		350	700	1050	1750	-
10 x 10 x 0,6		300	600	900	1500	2400
15 x 15 x 0,7		200	400	600	1000	1600
20 x 20 x 0,8		150	300	450	750	1200
20 x 30 x 0,8		130	260	390	650	1040
30 x 30 x 0,9		115	230	345	575	920
40 x 40 x 1,0		95	190	285	475	760
50 x 50 x 1,0		75	150	225	375	600

VOC Remarks

VOC (volatile organic compound) emissions < 20 µg/m³

Packages

Plastic bags containing 5kg

Notes

Technical details, properties, recommendations and information on BAUSKIN products are supplied in good faith. They are based on the company's research and experience, provided that they are stored and applied under normal conditions. As the method of using materials as well as project and environment conditions are beyond the control of the company in each individual application setting, the product user is held solely responsible for the result of application. No responsibility under any legitimate relationship can be substantiated against the company, based on the information set out hereunder. Product users are advised to refer to the latest revision of the technical manuals available.

Precautions and safety

The product contains cement and is classified as an irritant. No special precautions are necessary for product application except for standard precautions applicable to all construction operations i.e. using gloves and goggles; preventing prolonged skin contact; etc. In case of eye contact, immediately wash with plenty of water and seek medical advice if necessary. Collect empty bags and plastic covers and dispose of in refuse bins designated for this purpose. Consult instructions for safe use indicated on product packaging. For more information please refer to the material safety data sheet of the specific product.

Exclusive distribution for Greece:

BAUFOX Ltd
Email: info@baufox.com
www.baufox.com

Exclusive distribution for Cyprus:

ALTO CEMENTOCHEMICA KA Ltd
Email: info@altocy.com
www.altocy.com

Frankfurt, Reg. No 312310 QM
Qualitätsmanagementsystem
Zertifiziert nach DIN EN ISO 9001



TDS_BAU 08_12.2022

